

# SBS Modified Bitumen Membrane



## RUBEROID® GAF HW Granule Membrane



ITEM CODE: 3750

### Description:

RUBEROID® HW Granule membrane is a tough, resilient SBS modified bitumen membrane that can be installed without the use of hot asphalt. Its core is a strong non-woven polyester mat that is coated with an SBS polymer-modified asphalt and surfaced with mineral granules.

### Uses:

RUBEROID® HW Granule membrane is designed for new roofing and re-covering applications, as well as the construction of flashings. RUBEROID® HW Granule membrane is also a suitable product for repairs of built-up roofing membranes or other modified bitumen systems.

### Advantages:

- Lighter weight — installed roof designs weigh less than 2 pounds per square foot.
- Durability — specially formulated modified asphalt gives RUBEROID® HW Granule membrane lasting performance.
- Flexibility — specially formulated poly burn-off film allows for easy installation. Heat welding allows for kettle-free operation. Available with black or white granules.
- Resilience — the polyester mat core helps resist splits and tears due to its pliability and elongation characteristics.
- Product warranties and system guarantees are available. Contact your local sales representative for requirements, availability, and limitations. See warranties and guarantees on [gaf.com](http://gaf.com) for complete coverage and restrictions.

### Storage and Handling:

To prevent damage, support rolls on end in an upright position and store in a clean, dry location, covering as necessary to protect from environmental damage. Monitor environmental conditions during storage, handling, and application.

### Testing and Approvals:

- Classified by UL in accordance with ANSI/UL 790. Refer to UL Product iQ for specific assemblies.
- FM Approved — refer to [roofnav.com](http://roofnav.com) for approved assemblies.
- Miami-Dade County Product Control Approved.
- State of Florida Approved.
- UL Evaluation Report UL ER1306-02.
- Texas Department of Insurance Report RC-49.
- Meets or exceeds ASTM D6164 Type I, Grade G.
- For additional information, contact GAF Design Services at 1-877-423-7663 or [designservices@gaf.com](mailto:designservices@gaf.com).

### Product Specifications:

ASTM D6164 Type I, Grade G	
Roll Size*	107.3 ft. <sup>2</sup> (10.0 m <sup>2</sup> )
Roll Length	32' 6" (10.0 m)
Roll Width	39.625" (1.0 m)
Roll Weight	105 lb. (47.6 kg)
Roll Thickness	150 mils (3.8 mm)
Rolls per Pallet	25
Full Pallet Weight	2,675 lb. (1,213.4 kg)
Reinforcement	Polyester
Top Side Surfacing	Granule
Bottom Side Surfacing	Film

\* Roll size as reported represents actual membrane dimensions and does not calculate installation using side and end lap recommendations.



### Physical Properties:

Property	Standard Minimum Value	GAF Value
Thickness, min. mils (mm), Grade G	130 (3.3)	150 (3.8)
Net mass/unit area, min. g/m <sup>2</sup> (lb./100 ft. <sup>2</sup> )	3,661 (75)	4,638 (95)
Bottom coating thickness, heat-welding application products, min. mm (mils)	1.0 (40)	1.1 (44)
Peak load at -18 +/-2° C (0 +/-3.6° F), MD and CMD, min. before and after heat conditioning, kN/m (lbf/in.)	MD - 12.3 (70) CMD - 12.3 (70)	MD - 22.8 (130) CMD - 17.5 (100)
Elongation at -18 +/-2° C (0 +/-3.6° F), MD and CMD, min. at peak load, before and after heat conditioning, (%)	MD - 20.0 CMD - 20.0	MD - 40.0 CMD - 45.0
Peak load at 23 +/-2° C (73.4 +/-3.6° F), MD and CMD, min. before and after heat conditioning, kN/m (lbf/in.)	MD - 8.8 (50) CMD - 8.8 (50)	MD - 17.5 (100) CMD - 11.4 (65)
Elongation at 23 +/-2° C (73.4 +/-3.6° F), MD and CMD, min. at peak load, before and after heat conditioning, (%)	MD - 35.0 CMD - 35.0	MD - 45.0 CMD - 50.0
Ultimate elongation 23 +/-2° C (73.4 +/-3.6° F), MD and CMD, min. before and after heat conditioning, (%)	MD - 38.0 CMD - 38.0	MD - 60.0 CMD - 75.0
Tear strength at 23 +/-2° C (73.4 +/-3.6° F), min. N (lbf)	246 (55)	578 (130)
Low-temperature flexibility, max. before and after heat conditioning, ° C (° F)	-18 (0)	-20 (-4)
Dimensional stability, max. (%)	1.00	0.25
Compound stability at 102° C (215° F)	No Failures	No Failures
Granule embedment, max. (g)	2.0	1.0

Note: Values stated are average values and subject to normal manufacturing variation. These values are not guaranteed and are provided solely as a guide.



Visit [gaf.com](http://gaf.com)

We protect what matters most™

