

FR SBS Polymer-Modified Membrane



RUBEROID® GAF MopPlus GranuleFR Membrane



ITEM CODE: 3865

Description:

RUBEROID® Mop Plus Granule FR membrane is a premium, heavy-duty, fire-rated modified bitumen membrane manufactured to stringent GAF specifications. Its core is a strong, resilient non-woven polyester mat that is coated with SBS polymer-modified asphalt and surfaced with mineral granules.

Uses:

RUBEROID® Mop Plus Granule FR membrane is designed for new roofing and reroofing applications where long-term roof system performance is specified.

Advantages:

- Lighter weight — installed premium roof designs weigh less than 3 pounds per square foot.
- Resilience — the membrane's heavyweight polyester mat core helps resist splits and tears due to its pliability and elongation characteristics.
- Durability — specially formulated modified asphalt gives RUBEROID® Mop Plus Granule FR membrane lasting performance.
- Product warranties and system guarantees are available. Contact your local sales representative for requirements, availability, and limitations. See warranties and guarantees on gaf.com for complete coverage and restrictions.

Storage and Handling:

To prevent damage, support rolls on end in an upright position and store in a clean, dry location, covering as necessary to protect from environmental damage. Monitor environmental conditions during storage, handling, and application.

Testing and Approvals:

- Classified by UL in accordance with ANSI/UL 790, including as a component of Class A fire resistance-rated roofing assemblies. Refer to UL Product iQ for specific assemblies.
- FM Approved — refer to roofnav.com for approved assemblies.
- Miami-Dade County Product Control Approved.
- State of Florida Approved.
- UL Evaluation Report UL ER1306-02.
- Texas Department of Insurance Report RC-49.
- Meets or exceeds ASTM D6164 Type II, Grade G.
- For additional information, contact GAF Design Services at 1-877-423-7663 or designservices@gaf.com.

Product Specifications:

ASTM D6164 Type II, Grade G	
Roll Size*	107.3 ft. ² (10.0 m ²)
Roll Length	32' 6" (10.0 m)
Roll Width	39.625" (1.0 m)
Roll Weight	100 lb. (45.4 kg)
Roll Thickness	155 mils (3.9 mm)
Rolls per Pallet	25
Full Pallet Weight	2,550 lb. (1,156.7 kg)
Reinforcement	Polyester
Top Side Surfacing	Granule
Bottom Side Surfacing	Sand

* Roll size as reported represents actual membrane dimensions and does not calculate installation using side and end lap recommendations.



Physical Properties:

Property	Standard Minimum Value	GAF Value
Thickness, min. mm (mils), Grade G	130 (3.3)	155 (3.9)
Net mass/unit area, min. g/m ² (lb./100 ft. ²)	4,394 (90)	4,638 (95)
Bottom coating thickness, heat-welding application products, min. mm (mils)	1.0 (40)	1.0 (40)
Peak load at -18 +/-2° C (0 +/-3.6° F), MD and CMD, min. before and after heat conditioning, kN/m (lbf/in.)	MD - 17.5 (100) CMD - 17.5 (100)	MD - 22.8 (130) CMD - 24.5 (140)
Elongation at -18 +/-2° C (0 +/-3.6° F), MD and CMD, min. at peak load, before and after heat conditioning, (%)	MD - 20.0 CMD - 20.0	MD - 50.0 CMD - 60.0
Peak load at 23 +/-2° C (73.4 +/-3.6° F), MD and CMD, min. before and after heat conditioning, kN/m (lbf/in.)	MD - 12.3 (70) CMD - 12.3 (70)	MD - 21.9 (125) CMD - 17.5 (100)
Elongation at 23 +/-2° C (73.4 +/-3.6° F), MD and CMD, min. at peak load, before and after heat conditioning, (%)	MD - 50.0 CMD - 50.0	MD - 65.0 CMD - 80.0
Ultimate elongation 23 +/-2° C (73.4 +/-3.6° F), MD and CMD, min. before and after heat conditioning, (%)	MD - 60.0 CMD - 60.0	MD - 70.0 CMD - 85.0
Tear strength at 23 +/-2° C (73.4 +/-3.6° F), min. N (lbf)	311 (70)	667 (150)
Low-temperature flexibility, max. before and after heat conditioning, ° C (° F)	-18 (0)	-18 (0)
Dimensional stability, max. (%)	1.00	0.45
Compound stability at 102° C (215° F)	No Failures	No Failures
Granule embedment, max. ()	2.0	0.5

Note: Values stated are average values and subject to normal manufacturing variation. These values are not guaranteed and are provided solely as a guide



Visit gaf.com

We protect what matters most™

